

1. (original) Acoustically effective nonwoven (1) for linings of motor vehicles, comprising a porous fibrous skeleton (2) made of coarse fibers (8), in particular comprising staple fibers or spunbonded fibers, and which fibrous skeleton (2) has a continuously changing weight quota of melted on microfibrous material (7) in a front and/or rear surface region (4, 10), said melted on microfibrous material (7) clinging to the coarse fibers (8) and bonding these in such a manner that the nonwoven (1) has a predetermined air flow resistance and is stiffened at least in its surface region (4, 10).
2. (original) Nonwoven according to claim 1, wherein the coarse fibers (8) have a titre of more than 1 dtex, in particular in the range of 1 to 35 dtex, and preferably a titre of 6 to 17 dtex.
3. (currently amended) Nonwoven according to ~~claims 1 or 2~~, claim 1, wherein the coarse fibers (8) are spunbonded fibers and in particular are made of a polyester, a polypropylene or a polyamide, and preferably are made of PET.
4. (currently amended) Nonwoven according to ~~one of claims 1 to 3~~, claim 1, wherein said nonwoven (1) comprises non-melted on microfibers (9).
5. (original) Nonwoven according to claim 4, wherein the non-melted on microfibers (9) have a titre in the range of 0.01 to 1.0 dtex, preferably a titre of 0.1 to 0.6 dtex and typically a titre of around 0.2 dtex.
6. (currently amended) Nonwoven according to ~~one of claims 1 to 5~~, claim 1, wherein the microfibrous material (7) is a meltblown fibrous material, in particular is made of a polyester, a co-polyester, a polyamide, a co-polyamide, a polypropylene, a co-polypropylene or similar, and preferably is made of PET or Co-PET.

ATTACHMENT B

7. (currently amended) Nonwoven according to ~~one of claims 1 to 6~~, claim 1, wherein the coarse fibers (8) have a higher melting point than the microfibrinous material (7).
- 5
8. (currently amended) Nonwoven according to ~~one of claims 1 to 7~~, claim 1, wherein the air flow resistance in the surface region (4) of the fibrous nonwoven (1) has a value of between 200 to 5000, in particular 800 to 2500 and preferably 1400
- 10 Nsm⁻³.
9. (currently amended) Nonwoven according to ~~one of claims 1 to 8~~, claim 1, wherein the bending stiffness (B) of the fibrous nonwoven (1) has a value of between 0.005 and 10 Nm and in
- 15 particular has a value of between 0.025 to 6.0 Nm.
10. (currently amended) Nonwoven according to ~~one of claims 1 to 9~~, claim 1, wherein said nonwoven is combined with at least one further nonwoven.
- 20
11. (currently amended) Nonwoven according to ~~one of claims 1 to 10~~, claim 1, wherein said nonwoven is provided with an air impermeable layer.
- 25
12. (currently amended) Nonwoven according to ~~one of claims 1 to 11~~, claim 1, wherein said nonwoven is provided with a decorative layer.
- 30